

**CAN BE USED ON:**

- Concrete Surfaces
- Asphalt Surfaces
- Wood Surfaces
- Basements
- Sidewalks
- Garages
- Driveways
- Patios

**PRODUCT ADVANTAGES:**

- Resists hot tire pick-up
- Highly water-resistant
- High durability enamel

**GORILLA SPORTKOTE®** system is an economical, durable, easy to apply, acrylic finishing system for exterior concrete and asphalt surfaces such as tennis, handball and basketball courts. SportKote is also an excellent choice for non-skid surfaces on concrete stairs and walkways, as well as wooden and properly prepared metal surfaces. It is available in several colors and also available in custom colors.

**READ AND FOLLOW ALL DIRECTIONS:** Surfaces must be clean, dry, and sound; contaminants such as dirt, dust, grease, wax, oils, soap film, rust, mold & mildew, bond breakers, curing compounds, and loose, peeling paint must be removed before priming or painting. Repair holes & cracks with appropriate patching material.

**PRECAUTION:** Do not freeze. Wear protective clothing and eyewear during application of this product. Do not transport on passenger seats or inside passenger compartment of any vehicle. Store product in cargo area of vehicle, and secure with protective cloths to prevent accidental spill damage. Do not store at temperature above 100°F (37°C). Do not use in drinking water or food systems.

**PREPARATION:** Do not thin. Surface temperature must be a minimum of 55°F and rising. Do not apply if heavy dew or rain is expected within 12 hours. **All surfaces must be dry and free of dust, dirt, oil and other contaminants.** Remove with a solution of TSP (Trisodium Phosphate) and water. Rinse thoroughly, allow to dry. Acid etch concrete that is especially smooth, dense or treated with a curing or hardening compound. Use one part hydrochloric acid (muriatic acid) and three parts water. Apply and allow to stand for fifteen minutes. Rinse and allow to dry. New masonry should age 30 days before painting. New asphalt surfaces should cure a minimum of 10 days before application. Pressure washing entire surface is recommended for best results. Surfaces with mildew growth or stains must be cleaned with a bleach solution of two parts water to one part bleach prior to applying this product. Be certain all surfaces are thoroughly rinsed and dry prior to applying coating. Any areas where plant growth exists must be treated with an effective weed killer to prevent growth. Any cracks, low areas or other surface imperfections may be repaired by using a mix of SportKote and prepared mortar mix, blended to a smooth paste, suitable for troweling. A minimum of four hours drying time is necessary before the repair compound is top coated.

**APPLICATION:** Apply at 200 sq. ft. per gallon per coat, depending on the surface. Two coats are recommended at this spread rate for best results. Wait 72 hours (more if possible) before allowing vehicle traffic. May be applied by brush, roller or sprayer. Asphalt Surfaces: 1st coat should be applied at a rate of 200 sq. ft./gal. For best results, apply two coats with the second coat applied at right angles to the first. First coat must dry one to two hours before recoat. Concrete Surfaces: Properly prepared concrete should receive two coats of SportKote. Apply the first coat evenly over the entire surface. When properly cured, apply a second coat of SportKote at a rate of 150-200 sq. ft./gal.

To spray, up to ½ pint of water may be added to each gallon of paint. Use the following recommendation or equal as a guide: Tip: .013 - .017", Fan: 40° - 60° (8-12 inch fan), Pressure 1500-2000 PSI. Please note: This product may contain a slip-resistant aggregate, special tips and equipment may be required. Please refer to your equipment manufacturer for application details.

**TOOL & APPLICATOR CLEANING:** Clean immediately with warm, soapy water.

**AFTER CARE:** Allow 10 days after applying before washing. Use nonabrasive, mild detergent and cellulose sponge or warm baby wipes. Do not lean objects against freshly painted surfaces.

**SEE MSDS FOR ADDITIONAL INFORMATION.**

**TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS**

Weight Per Gallon	10.90lbs.
Solids by Weight	52%
Solids by Volume	48%
Gloss Reading at 60 °	6
Viscosity (ASTM D-2697)	95 KU
Film Dry Thickness	3.8 mil
Combustible Solvents	Ethylene Glycol
Consistency	Brush, spray or roller
Suggested Coverage (varies per substrate)	150-200 sq. ft./gal.
Cure Time (50% Relative Humidity, 70°F)	1 Hour (Foot Traffic: 4 Hours)
Full Cure (50% Relative Humidity, 70°F)	24-36 Hours
Application Temperatures	55°F
Clean-up Tools	Water
<b>APPROXIMATE SHIPPING WEIGHTS:</b> Note - all weights include container.	
1 gallon (3.8L)	12lbs.
(4) 1 gallon containers/case	48lbs.
5 gallons (18.9L)	60lbs.
55 drums (208.2L)	650lbs.

**FIRST AID:** If swallowed, gently wipe or rinse the inside of the mouth with water. Water may be given if person is alert. Do NOT induce vomiting. Get medical attention immediately. If skin/eye contact occurs, flush the affected areas with warm water for at least 15 minutes. Remove contact lens. A mild soap may be used on skin if available. If inhaled, remove from area to fresh air. If breathing is difficult, get medical attention immediately. Take MSDS or label information.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**CAUTION!**

**HARMFUL IF SWALLOWED. MAY CAUSE EYE, SKIN AND RESPIRATORY IRRITATION. USE WITH ADEQUATE VENTILATION. DO NOT TAKE INTERNALLY. KEEP CLOSED WHEN NOT IN USE. KEEP OUT OF REACH OF CHILDREN.**

**CALIF. PROP. 65 • CHEMICAL WARNING (CALIFORNIA HEALTH AND SAFETY CODE #25249.5 ET SEQ).** WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or reproductive harm. Use proper protection and adequate ventilation, when using product.

**VOC/VOS:** Actual 13.06 g/l. Regulatory 24.18 g/l.

Water	CAS # 7732-18-5
Latex Polymer	CAS # Mixture
Titanium	CAS # 13463-67-7
Calcium Carbonate	CAS # 1317-65-3
Silica Sand	CAS # 14808-60-7
Ethylene Glycol	CAS # 107-21-1

Product is asbestos free.

**WARRANTY AND DISCLAIMER:** For limited warranty and disclaimer information, contact the Sun Paints & Coatings corporate office at 1-800-247-9891.

